



AB-0716-T
TURT250029990
04-25

TEST REPORT

Page 1 of 17

REPORT NUMBER : TURT250029990

APPLICANT NAME Bigpoint Kırtasiye San. ve Tic.Ltd.Şti.

ADDRESS Merkez Mah. 29 Ekim Cad.No:53 Bahçelievler/İstanbul
Tel:0212 551 00 92 Fax:0212 551 09 57

Attention : Efe Yüksel (efe@bigpoint.com.tr)

SAMPLE DESCRIPTION : DOCUMENT FILE

- Sample 1:** One sample of Bigpoint Blue and Transparent A4 Envelopes Bag 11 Holdes
- Sample 2:** One sample of Bigpoint Black and Transparent A4 Envelopes Bag 11 Holdes
- Sample 3:** One sample of Bigpoint Yellow and Transparent A4 Envelopes Bag 11 Holdes
- Sample 4:** One sample of Bigpoint Orange and Transparent A4 Envelopes Bag 11 Holdes
- Sample 5:** One sample of Bigpoint Transparent A4 Document File
- Sample 6:** One sample of Bigpoint Red Coloured Snap-on A4 Document File
- Sample 7:** One sample of Bigpoint Yellow Coloured Snap-on A4 Document File
- Sample 8:** One sample of Bigpoint Blue and Transparent A4 Locked Document File
- Sample 9:** One sample of Bigpoint White and Transparent A4 Locked Document File
- Sample 10:** One sample of Blue Coloured A4 Size 13 Pockets Expanding File
- Sample 11:** One sample of Blue Coloured A4 Size 13 Pockets Little Size Gusseted File
- Sample 12:** One sample of Grey Coloured A4 Size 13 Pockets Gusseted Expanding File
- Sample 13:** One sample of Black Coloured A4 Size 13 Pockets Gusseted Expanding File
- Sample 14:** One sample of Blue Coloured Business Card Album 600 Capacited
- Sample 15:** One sample of Blue Coloured Business Card Album 480 Capacited
- Sample 16:** One sample of Black Coloured Business Card Album 600 Capacited
- Sample 17:** One sample of Black Coloured Business Card Album 480 Capacited

DATE IN : 18 March, 2025 (10:18)

RESUBMIT DATE: 24 March, 2025

DATE OUT : 02 April, 2025

Gaye CALIŞKAN
Customer Care Executive

Emre ÇALIK
Chemical Laboratory Manager

Intertek Test Hizmetleri A.Ş.
Merkez Mahallesi Sanayi Cad. No: 23 Altındağ Plaza Yenibosna 34197 - ISTANBUL / TURKEY
Phone : +90.212. 496 46 46 Fax : +90.212. 452 80 55
e-mail : intertekcg.turkiye@intertek.com
www.intertek-turkey.com



250029990

R E S U L T S

REPORT: TURT250029990

MODEL NO : 25BTS89-16
BRAND: BIG POINT
ITEM NO: BP238-25, BP238-15, BP244-01, BP244-35, BP251-35, BP251-45, BP251-55, BP251-90,
BP253-03, BP262-35, BP263-35, BP263-90, BP266-95, BP156, BP157
MANUFACTURER: GUANGDONG HOLLON PLASTIC TECHNOLOGY CO.,LTD.
COUNTRY OF ORIGIN: CHINA

RESULTS

REPORT: TURT250029990

Page 3 of 17

02 April, 2025

SAMPLE PHOTOS

Sample 1



Sample 2



Sample 3



Sample 4



Sample 5



Sample 6



RESULTS

REPORT: TURT250029990

Page 4 of 17

02 April, 2025

Sample 7



Sample 8



Sample 9



Sample 10



Sample 11



Sample 12



RESULTS

REPORT: TURT250029990

Page 5 of 17

02 April, 2025


Sample 13



Sample 14




Sample 15



Sample 16



Sample 17



Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No: 23 Altındağ Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax : +90.212. 452 80 55

e-mail : intertekcg.turkiye@intertek.com

www.intertek-turkey.com

RESULTS

Page 6 of 17

REPORT: TURT250029990

02 April, 2025

Part No	Tested Part
1	Transparent plastic file (Sample 1&2&3&4&5)
2	Blue plastic (Sample 1)
3	White textile loop (Sample 1&2&3&4&5)
4	White plastic hook (Sample 1&2&3&4&5)
5	Silver coating on file (Sample 1&2&3&4&5)
6	Grey plastic file(Sample 2)
7	Yellow plastic file (Sample 3)
8	Orange plastic file (Sample 4)
9	Red plastic file (Sample 6)
10	White plastic button (Sample 6&7)
11	Yellow plastic file (Sample 7)
12	Blue hard plastic (Sample 8)
13	Blue soft plastic (Sample 8)
14	Transparent plastic file (Sample 8&9)
15	White hard plastic (Sample 9)
16	White soft plastic (Sample 9)
17	Transparent plastic clasp (Sample 10)
18	White hard plastic clasp (Sample 10&11&12)
19	Transparent plastic file (Sample 10&11&12&13)
20	Blue plastic file(Sample 10&11)
21	Cream hard plastic clasp (Sample 10)
22	Dark blue plastic clasp (Sample 11)
23	Grey plastic file (Sample 12)
24	Grey plastic clasb (Sample 12)
25	Multicolor paper (Sample 13)
26	Black elastic tape (Sample 13)
27	Black plastic file (Sample 13)
28	Black plastic button (Sample 13)
29	Transparent inner soft plastic (Sample 14&15)
30	Black plastic cover (Sample 16&17)
31	Silver metal hook (Sample 14&15&16&17)
32	Silver metal part (Sample 14&15&16&17)
33	Transparent inner hard plastic (Sample 14&15&16&17)
34	White/black paper (Sample 14&15&16&17)
35	Transparent plastic page (Sample 14&15&16&17)
36	Navy plastic cover (Sample 14&15)
37	Silver metal clips (Sample 14&15&16&17)
38	Silver metal nail (Sample 14&15&16&17)
39	Silver metal nail shank (Sample 14&15&16&17)

Remark: Only suitable parts tested for the related tests.

RESULTS

Page 7 of 17

REPORT: TURT250029990

02 April, 2025

RESULTS :

Analysis Parameter	Reference Analysis Method	PASS	FAIL	Norm Limit	Standard for Norm Limit	Failed item
DETERMINATION OF CERTAIN AROMATIC AMINES DERIVED FROM AZO	EN ISO 14362-1 determined by GC-MS, HPLC-MS	P	-	<30 ppm	REACH ANNEX XVII	-
POLYCYCLIC AROMATIC HYDROCARBONS (PAHS) ANALYSIS	In-House Method – "IHTM AL.2.032 Rev.15" (Based on AfPS GS and EN 17132) (Using GC-MS)	P	-	1 ppm	REACH ANNEX XVII	-
DETERMINATION OF CADMIUM CONTENT	In-House Method – "IHTM AL.2.222. Rev.10" (With reference to EPA 3050B, EPA 3051A, EPA 3052) (Using ICP-OES)	P	-	Metal, Plastic 100 ppm; Coating, print, dye 1000 ppm	REACH ANNEX XVII	-
DETERMINATION OF LEAD CONTENT	In-House Method – "IHTM AL.2.222. Rev.10" (With reference to EPA 3050B, EPA 3051A, EPA 3052) (Using ICP-OES)	P	-	500 ppm (0.05%)	REACH ANNEX XVII	-
TRIBUTYL TIN (TBT) CONTENT	In-House Method – "IHTM AL.2.030 Rev.13" (based on ISO 17353) (Using GC-MS)	P	-	1000 ppm (0.1%)	REACH ANNEX XVII	-
RELEASE OF NICKEL FOR COATED ITEM	BS EN 12472 & EN 1811 by ICP-MS Determination	NA	NA	<0.88	REACH ANNEX XVII	-
DMFU CONTENT	In-House Method – "IHTM AL.2.136. Rev.10" (Based on BS EN 17130) (Using GC-MS)	P	-	1000 ppm (0.1%)	REACH ANNEX XVII	-
DETERMINATION OF BISPHENOL A (BPA) CONTENT	In-House Method - "IHTM AL.2.330 Rev.5" (Using LC-MS-MS)	NA	NA	≤0.02 ppm	REACH ANNEX XVII	-
DETERMINATION OF CR+VI CONTENT	ISO 17075-2 with HPLC Determination	NA	NA	3 ppm	REACH ANNEX XVII	-
DETERMINATION OF DIETHYLENE GLYCOL MONOBUTYL (DEGBE)	In-house method – "IHTM AL.2.409. Rev.2" (Based on EPA 5000 & EPA 5021A) (Using GC-MS Headspace)	NA	NA	≤(3%)	REACH ANNEX XVII	-
TOLUENE CONTENT	In-house method – "IHTM AL.2.409. Rev.2" (Based on EPA 5000 & EPA 5021A) (Using GC-MS Headspace)	NA	NA	≤1000 ppm (0.1%)	REACH ANNEX XVII	-

RESULTS

REPORT: TURT250029990

02 April, 2025

RESULTS :

Analysis Parameter	Reference Analysis Method	PASS	FAIL	Norm Limit	Standard for Norm Limit	Failed item
VINYL CHLORIDE MONOMER(VCM) CONTENT	In-House Method – “IHTM AL.2.393. Rev.1”(based on ISO 6401 and GB/T 4615) (using GC-MS-HS)	NA	NA	No Requirement	REACH ANNEX XVII	-
DETERMINATION OF LEAD CARBONATE / SULFATE CONTENT	In-House Method – “IHTM AL.2.222. Rev.10” (With reference to EPA 3050B, EPA 3051A, EPA 3052) (Using ICP-OES)	-	-	SEE RESULT	REACH ANNEX XVII	-

P = MEETS BUYER' S REQUIREMENT (GEÇTİ) / F = DOES NOT MEET BUYER' S REQUIREMENT (KALDI) / NR = NO REQUIREMENT (SINIR DEĞER BELİRTİLMEDİ) / SC=STILL CONTINUES (TEST İŞLEMİ DEVAM EDİYOR) / X=NOT PERFORMED (TEST EDİLMEDİ) / I = INCONCLUSIVE / NC = NO COMMENT / NA= NOT APPLICABLE

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Nor could it be used for PR activities. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>. Testing reports without signature are not valid. The sample has been provided by the customer and the results apply to the sample as received. Sample information is supplied by the customer. Unless otherwise requested, this laboratory applies shared risk decision rule. Unless otherwise is specified, all Pass or Fail results are given without uncertainty considered. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025 and TÜRKAK accreditation requirements.. Tests marked (*) in this test report are not included in the TÜRKAK accreditation schedule for this laboratory. Intertek accredited by TÜRKAK under registration number [AB-0716-T] for [TS EN ISO IEC 17025] as test laboratory. Turkish Accreditation Agency (TÜRKAK) is a signatory to the European co-operation for Accreditation (EA) Multilateral Agreement (MLA) and to the International Laboratory Accreditation Cooperation (ILAC) Mutual Recognition Arrangement (MRA) for the recognition of test reports.

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No: 23 Altındağ Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax : +90.212. 452 80 55

e-mail : intertekcg.turkiye@intertek.com

www.intertek-turkey.com

RESULTS

Page 9 of 17

REPORT: TURT250029990

02 April, 2025

DETECTION OF AMINES DERIVED FROM AZOCOLOURANTS AND AZODYES

EN ISO 14362-1 determined by GC-MS, HPLC-MS

By Gas Chromatographic - Mass Spectrometric (GC-MS) And High Performance Liquid Chromatographic (HPLC) Analysis.

Part 26

1-Black elastic tape (with extraction)

<30 ppm

2- Black elastic tape (without extraction)

<u>FORBIDDEN AMINE</u>	<u>CAS NO</u>	<u>RESULT</u>	
		<u>1</u>	<u>2</u>
4-AMINOBIIPHENYL	92-67-1	N	N
BENZIDINE	92-87-5	N	N
CHLORO-O-4-CHLOR-O-TOLUIDINE	95-69-2	N	N
2-NAPHTHYLAMINE	91-59-8	N	N
*O-AMINOAZOTOLUENE	97-56-3	N	N
*2-AMINO-4-NITROTOLUENE	99-55-8	N	N
P-CHLOROANILINE	106-47-8	N	N
2,4-DIAMINOANISOLE	615-05-4	N	N
4,4'-DIAMINOBIIPHENYLMETHANE	101-77-9	N	N
3,3'-DICHLOBENZIDINE	91-94-1	N	N
3,3'-DIMETHOXYBENZIDINE	119-90-4	N	N
3,3'-DIMETHYLBENZIDINE	119-93-7	N	N
3,3'-DIMETHYL-4,4' DIAMINOBIIPHENYLMETHANE	838-88-0	N	N
P-CRESIDINE	120-71-8	N	N
4,4'-METHYLENE-BIS-(2 CHLOROANILINE)	101-14-4	N	N
4,4'-OXYDIANILINE	101-80-4	N	N
4,4'-THIODIANILINE	139-65-1	N	N
O-TOLUIDINE	95-53-4	N	N
2,4-TOLUYLENDIAMINE	95-80-7	N	N
2,4,5-TRIMETHYLANILINE	137-17-7	N	N
O-ANISIDINE	90-04-0	N	N
**P-AMINOAZOBENZENE	60-09-3	N	N

NOTE:

- 1)The amines o-amino-azotoluene and 2-amino-4-nitrotoluene are detected by its splitted product o-toluidine and 2,4- toluenylenediamine.
- 2)Azo colorants that are able to form 4-aminoazobenzene, generate under the condition of this method aniline and 1,4- phenylenediamine . The presence of these colorants can not be reliably ascertained without additional information, e.g. chemical structure of the colorant used.
- 3)According to EN 14362-1:2017, separate test is suggested to ascertain the compliance for result of mixed test in the range between 5 ppm and 30 ppm.
- 4)Azocolourants Content Requirement In Annex XVII Item 43 Of The REACH Regulation (EC) NO. 1907/2006 & Amendment No. 552/2009 and 126/2013 (Formerly Known As Directive 2002/61/EC
- 5) According to the official method EN 14362-1:2017, if 4-Aminodiphenyl or 2-Naphthylamine or 2,4-Diaminoanisoole is found exceeding requirement, the use of forbidden Azo colourants cannot be ascertained without additional information e.g. The chemical structure of the colourant used.

< =	Less Than
N=	Not Detected
Requirement=	30 ppm
ppm(part per million)=	mg/ kg
Detection Limit =	5 ppm
Estimated Total Uncertainty=	Textile: ±17% Polyester: ±16%

RESULTS

Page 10 of 17

REPORT: TURT250029990

02 April, 2025

POLYCYCLIC AROMATIC HYDROCARBONS (PAHs) ANALYSIS

In-House Method – "IHTM AL.2.032 Rev.15" (Based on AfPS GS and EN 17132) (Using GC-MS)

	Part 1&2&4	RESULT (mg/kg)	REQUIREMENT
1	Benzo (a) pyrene	Not Detected	1 ppm
2	Benzo (e) pyrene	Not Detected	1 ppm
3	Benzo (a) anthracene	Not Detected	1 ppm
4	Benzo (b) fluoranthene	Not Detected	1 ppm
5	Benzo (j) fluoranthene	Not Detected	1 ppm
6	Benzo (k) fluoranthene	Not Detected	1 ppm
7	Chrysene	Not Detected	1 ppm
8	Dibenzo (a,h) anthracene	Not Detected	1 ppm

	Part 6&7&8	RESULT (mg/kg)	REQUIREMENT
1	Benzo (a) pyrene	Not Detected	1 ppm
2	Benzo (e) pyrene	Not Detected	1 ppm
3	Benzo (a) anthracene	Not Detected	1 ppm
4	Benzo (b) fluoranthene	Not Detected	1 ppm
5	Benzo (j) fluoranthene	Not Detected	1 ppm
6	Benzo (k) fluoranthene	Not Detected	1 ppm
7	Chrysene	Not Detected	1 ppm
8	Dibenzo (a,h) anthracene	Not Detected	1 ppm

	Part 9&10&11	RESULT (mg/kg)	REQUIREMENT
1	Benzo (a) pyrene	Not Detected	1 ppm
2	Benzo (e) pyrene	Not Detected	1 ppm
3	Benzo (a) anthracene	Not Detected	1 ppm
4	Benzo (b) fluoranthene	Not Detected	1 ppm
5	Benzo (j) fluoranthene	Not Detected	1 ppm
6	Benzo (k) fluoranthene	Not Detected	1 ppm
7	Chrysene	Not Detected	1 ppm
8	Dibenzo (a,h) anthracene	Not Detected	1 ppm

ppm (part per million) = mg / kg
Detection Limit = 0.1 ppm

Estimated Total Uncertainty = (Textile:±15%, Plastic:±17%)

RESULTS

Page 11 of 17

REPORT: TURT250029990

02 April, 2025

POLYCYCLIC AROMATIC HYDROCARBONS (PAHs) ANALYSIS

In-House Method – "IHTM AL.2.032 Rev.15" (Based on AfPS GS and EN 17132) (Using GC-MS)

	Part 12&13&14	RESULT (mg/kg)	REQUIREMENT
1	Benzo (a) pyrene	Not Detected	1 ppm
2	Benzo (e) pyrene	Not Detected	1 ppm
3	Benzo (a) anthracene	Not Detected	1 ppm
4	Benzo (b) fluoranthene	Not Detected	1 ppm
5	Benzo (j) fluoranthene	Not Detected	1 ppm
6	Benzo (k) fluoranthene	Not Detected	1 ppm
7	Chrysene	Not Detected	1 ppm
8	Dibenzo (a,h) anthracene	Not Detected	1 ppm

	Part 15&16&17	RESULT (mg/kg)	REQUIREMENT
1	Benzo (a) pyrene	Not Detected	1 ppm
2	Benzo (e) pyrene	Not Detected	1 ppm
3	Benzo (a) anthracene	Not Detected	1 ppm
4	Benzo (b) fluoranthene	Not Detected	1 ppm
5	Benzo (j) fluoranthene	Not Detected	1 ppm
6	Benzo (k) fluoranthene	Not Detected	1 ppm
7	Chrysene	Not Detected	1 ppm
8	Dibenzo (a,h) anthracene	Not Detected	1 ppm

	Part 18&19&20	RESULT (mg/kg)	REQUIREMENT
1	Benzo (a) pyrene	Not Detected	1 ppm
2	Benzo (e) pyrene	Not Detected	1 ppm
3	Benzo (a) anthracene	Not Detected	1 ppm
4	Benzo (b) fluoranthene	Not Detected	1 ppm
5	Benzo (j) fluoranthene	Not Detected	1 ppm
6	Benzo (k) fluoranthene	Not Detected	1 ppm
7	Chrysene	Not Detected	1 ppm
8	Dibenzo (a,h) anthracene	Not Detected	1 ppm

ppm (part per million) = mg / kg
Detection Limit = 0.1 ppm

Estimated Total Uncertainty = (Textile:±15%, Plastic:±17%)

RESULTS

Page 12 of 17

REPORT: TURT250029990

02 April, 2025

POLYCYCLIC AROMATIC HYDROCARBONS (PAHs) ANALYSIS

In-House Method – "IHTM AL.2.032 Rev.15" (Based on AfPS GS and EN 17132) (Using GC-MS)

	Part 21&22&23	RESULT (mg/kg)	REQUIREMENT
1	Benzo (a) pyrene	Not Detected	1 ppm
2	Benzo (e) pyrene	Not Detected	1 ppm
3	Benzo (a) anthracene	Not Detected	1 ppm
4	Benzo (b) fluoranthene	Not Detected	1 ppm
5	Benzo (j) fluoranthene	Not Detected	1 ppm
6	Benzo (k) fluoranthene	Not Detected	1 ppm
7	Chrysene	Not Detected	1 ppm
8	Dibenzo (a,h) anthracene	Not Detected	1 ppm

	Part 24&27&28	RESULT (mg/kg)	REQUIREMENT
1	Benzo (a) pyrene	Not Detected	1 ppm
2	Benzo (e) pyrene	Not Detected	1 ppm
3	Benzo (a) anthracene	Not Detected	1 ppm
4	Benzo (b) fluoranthene	Not Detected	1 ppm
5	Benzo (j) fluoranthene	Not Detected	1 ppm
6	Benzo (k) fluoranthene	Not Detected	1 ppm
7	Chrysene	Not Detected	1 ppm
8	Dibenzo (a,h) anthracene	Not Detected	1 ppm

	Part 26	RESULT (mg/kg)	REQUIREMENT
1	Benzo (a) pyrene	Not Detected	1 ppm
2	Benzo (e) pyrene	Not Detected	1 ppm
3	Benzo (a) anthracene	Not Detected	1 ppm
4	Benzo (b) fluoranthene	Not Detected	1 ppm
5	Benzo (j) fluoranthene	Not Detected	1 ppm
6	Benzo (k) fluoranthene	Not Detected	1 ppm
7	Chrysene	Not Detected	1 ppm
8	Dibenzo (a,h) anthracene	Not Detected	1 ppm

ppm (part per million) = mg / kg
Detection Limit = 0.1 ppm

Estimated Total Uncertainty = (Textile:±15%, Plastic:±17%)

RESULTS

Page 13 of 17

REPORT: TURT250029990

02 April, 2025

POLYCYCLIC AROMATIC HYDROCARBONS (PAHs) ANALYSIS

In-House Method – "IHTM AL.2.032 Rev.15" (Based on AfPS GS and EN 17132) (Using GC-MS)

	Part 29&30&33	RESULT (mg/kg)	REQUIREMENT
1	Benzo (a) pyrene	Not Detected	1 ppm
2	Benzo (e) pyrene	Not Detected	1 ppm
3	Benzo (a) anthracene	Not Detected	1 ppm
4	Benzo (b) fluoranthene	Not Detected	1 ppm
5	Benzo (j) fluoranthene	Not Detected	1 ppm
6	Benzo (k) fluoranthene	Not Detected	1 ppm
7	Chrysene	Not Detected	1 ppm
8	Dibenzo (a,h) anthracene	Not Detected	1 ppm

	Part 35&36	RESULT (mg/kg)	REQUIREMENT
1	Benzo (a) pyrene	Not Detected	1 ppm
2	Benzo (e) pyrene	Not Detected	1 ppm
3	Benzo (a) anthracene	Not Detected	1 ppm
4	Benzo (b) fluoranthene	Not Detected	1 ppm
5	Benzo (j) fluoranthene	Not Detected	1 ppm
6	Benzo (k) fluoranthene	Not Detected	1 ppm
7	Chrysene	Not Detected	1 ppm
8	Dibenzo (a,h) anthracene	Not Detected	1 ppm

ppm (part per million) = mg / kg
Detection Limit = 0.1 ppm

Estimated Total Uncertainty = (Textile:±15%, Plastic:±17%)

RESULTS

Page 14 of 17

REPORT: TURT250029990

02 April, 2025

DETERMINATION OF CADMIUM CONTENT

In-House Method – "IHTM AL.2.222. Rev.10" (With reference to EPA 3050B, EPA 3051A, EPA 3052) (Using ICP-OES)

	RESULTS	REQUIREMENT
Part 1&2	Not Detected	100 ppm (0.01%)
Part 4&36	Not Detected	100 ppm (0.01%)
Part 5	Not Detected	100 ppm (0.01%)
Part 6&7&8	Not Detected	100 ppm (0.01%)
Part 9&10&11	Not Detected	100 ppm (0.01%)
Part 12&13&14	Not Detected	100 ppm (0.01%)
Part 15&16&17	Not Detected	100 ppm (0.01%)
Part 18&19&20	Not Detected	100 ppm (0.01%)
Part 21&22&23	Not Detected	100 ppm (0.01%)
Part 24	Not Detected	100 ppm (0.01%)
Part 25	Not Detected	100 ppm (0.01%)
Part 26	Not Detected	100 ppm (0.01%)
Part 27&28&29	Not Detected	100 ppm (0.01%)
Part 30&33&35	Not Detected	100 ppm (0.01%)
Part 34	Not Detected	100 ppm (0.01%)

ppm: =parts per million (mg/kg)
Detection Limit : =8 ppm
% =Percentage based on dry weight of sample

REMARK : As per Cadmium Content Requirement in Annex XVII item 23 of the REACH Regulation (EC) No: 1907/2006 (Formerly Known as Directive 91/338/EEC), Acid Digestion Method was used Total Cadmium Content was determined by ICP-OES

Estimated Total Uncertainty=(Dye: ±16%, Glass: ±16%, Metal: ±16%, Plastic: ±16%, Textile: ±15%)

RESULTS

Page 15 of 17

REPORT: TURT250029990

02 April, 2025

DETERMINATION OF LEAD CONTENT

In-House Method – "IHTM AL.2.222. Rev.10" (With reference to EPA 3050B, EPA 3051A, EPA 3052) (Using ICP-OES)

	RESULTS	REQUIREMENT
Part 1&2	Not Detected	500 ppm (0.05%)
Part 3	Not Detected	500 ppm (0.05%)
Part 4&36	Not Detected	500 ppm (0.05%)
Part 5	Not Detected	500 ppm (0.05%)
Part 6&7&8	Not Detected	500 ppm (0.05%)
Part 9&10&11	Not Detected	500 ppm (0.05%)
Part 12&13&14	Not Detected	500 ppm (0.05%)
Part 15&16&17	Not Detected	500 ppm (0.05%)
Part 18&19&20	Not Detected	500 ppm (0.05%)
Part 21&22&23	Not Detected	500 ppm (0.05%)
Part 24	Not Detected	500 ppm (0.05%)
Part 25	Not Detected	500 ppm (0.05%)
Part 26	Not Detected	500 ppm (0.05%)
Part 27&28&29	Not Detected	500 ppm (0.05%)
Part 30&33&35	Not Detected	500 ppm (0.05%)
Part 31	Not Detected	500 ppm (0.05%)
Part 32	Not Detected	500 ppm (0.05%)
Part 34	Not Detected	500 ppm (0.05%)
Part 36	Not Detected	500 ppm (0.05%)
Part 37	Not Detected	500 ppm (0.05%)
Part 38	Not Detected	500 ppm (0.05%)
Part 39	Not Detected	500 ppm (0.05%)

ppm: =parts per million (mg/kg)
 Detection Limit : =8 ppm
 % =Percentage based on dry weight of sample

Estimated Total Uncertainty=(Dye: ±16%, Glass: ±16%, Metal: ±16%, Plastic: ±16%, Textile: ±15%)

RESULTS

Page 16 of 17

REPORT: TURT250029990

02 April, 2025

TRIBUTYL TIN (TBT) CONTENT

In-House Method – "IHTM AL.2.030 Rev.13" (based on ISO 17353) (Using GC-MS)

ETHANOL EXTRACTION, DERIVATISATION AND ANALYSIS BY GAS CHROMATOGRAPHY - MASS SPECTROPHOTOMETRY

	RESULTS	REQUIREMENT
Part 1&2&4	Not Detected	1000 ppm (0.1%)
Part 6&7&8	Not Detected	1000 ppm (0.1%)
Part 9&10&11	Not Detected	1000 ppm (0.1%)
Part 12&13&14	Not Detected	1000 ppm (0.1%)
Part 15&16&17	Not Detected	1000 ppm (0.1%)
Part 18&19&20	Not Detected	1000 ppm (0.1%)
Part 21&22&23	Not Detected	1000 ppm (0.1%)
Part 24&27&28	Not Detected	1000 ppm (0.1%)
Part 29&30&33	Not Detected	1000 ppm (0.1%)
Part 35&36	Not Detected	1000 ppm (0.1%)

ppm: parts per million (mg/kg)
Detection Limit : 0.050 ppm

Estimated Total Uncertainty =(Plastic:±19%; Leather:±19%)

RESULTS

Page 17 of 17

REPORT: TURT250029990

02 April, 2025

DMFU CONTENT

In-House Method – "IHTM AL.2.136. Rev.10" (Based on BS EN 17130) (Using GC-MS)

	RESULTS	REQUIREMENT
Part 1&2&4	Not Detected	<1000 ppm (0.1%)
Part 3&27	Not Detected	<1000 ppm (0.1%)
Part 6&7&8	Not Detected	<1000 ppm (0.1%)
Part 9&10&11	Not Detected	<1000 ppm (0.1%)
Part 12&13&14	Not Detected	<1000 ppm (0.1%)
Part 15&16&17	Not Detected	<1000 ppm (0.1%)
Part 18&19&20	Not Detected	<1000 ppm (0.1%)
Part 21&22&23	Not Detected	<1000 ppm (0.1%)
Part 24&27&28	Not Detected	<1000 ppm (0.1%)
Part 29&30&33	Not Detected	<1000 ppm (0.1%)
Part 35&36	Not Detected	<1000 ppm (0.1%)

ppm: parts per million (mg/kg)
Detection Limit : 0.1 ppm

Estimated Total Uncertainty =(Plastic:±19%; Leather:±19%)

END OF TEST REPORT