

## TEST RAPORU

**REPORT NUMBER :** TURT190127430  
**APPLICANT NAME** **Bilgi Dağ. Kitap Kırt. ve Büro Malz. Tic. Ltd. Şti.**  
**ADDRESS** Merkez Mah. 29 Ekim Cad.No:53 Bahçelievler/İstanbul  
Tel: 0212 551 00 92 Fax:0212 551 09 57  
**Attention: Efe Yüksel (efe@bilgi-dagitim.com)**  
**SAMPLE DESCRIPTION :** One sample of Transparent notebook cover  
**BUYER :** METRO BTS  
**DATE IN :** 12 July, 2019 (09:59)  
**DATE OUT :** 22 July, 2019  
**MANUFACTURER :** BİLGİ DAĞ KİTAP KIRT. VE BÜRO MALZ. TİC. LTD ŞTİ.  
**ITEM CODE :** BP790-25  
**PHOTO OF PRODUCT TESTED SAMPLE :**



**RESULTS :** See Attachment

*Begüm Nazlı Traş*

Begüm Nazlı Traş  
Customer Care Executive

*Zeynep AKIN*

Zeynep AKIN  
Chemical Laboratory Manager

**Intertek Test Hizmetleri A.Ş.**  
Merkez Mahallesi Sanayi Cad. No: 23 Altındağ Plaza Yenibosna 34197 - ISTANBUL / TURKEY  
Phone : +90.212. 496 46 46 Fax : +90.212. 452 80 55  
e-mail : intertekcg.turkiye@intertek.com  
www.intertek-turkey.com



190127430

**RESULTS :**

Analysis Parameter	Reference Analysis Method	PASS	FAIL	Norm Limit	Standard for Norm Limit	Tested Part
Migration Of Certain Elements	EN 71-3:2013+A3:2018	P	-	See Toxic Element Analysis	Toys Safety Directive	Part 1

P = MEETS BUYER' S REQUIREMENT / F = DOES NOT MEET BUYER' S REQUIREMENT / NR = NO REQUIREMENT / SC=STILL CONTINUES / X=NOT PERFORMED

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>. Testing reports without signature are not valid. The sample has been provided by the customer and the results apply to the sample as received. Sample information is supplied by the customer. Unless otherwise requested, this laboratory applies shared risk decision rule. Opinions and interpretations expressed herein are outside the scope of TÜRKAK accreditation. Tests marked (\*) in this test report are not included in the TÜRKAK accreditation schedule for this laboratory.

Part No	Tested Part
1	Transparent plastic with glue

Remark: Only suitable parts tested for the related tests.

## MIGRATION OF CERTAIN ELEMENTS

EN 71-3:2013+A3:2018

Acid extraction method was used and migration elements content were determined by Inductively Coupled Plasma-ICP\_MS.

	Results (mg/kg)				Detection Limit (mg/kg)	Requirements (mg/kg) Category III
	Part 1					
Antimony (Sb)	ND				0,125	560
Arsenic (As)	ND				0,125	47
Barium (Ba)	ND				0,125	18750
Cadmium (Cd)	ND				0,125	17
Chromium (III) **	ND				0,125	460
Chromium (VI) **	ND				0,125	0,2
Lead (Pb)	ND				0,125	23
Mercury (Hg)	ND				0,0125	94
Selenium (Se)	ND				0,125	460
Aluminium (Al)	ND				0,125	70000
Boron (B)	ND				0,125	15000
Cobalt (Co)	ND				0,125	130
Copper (Cu)	ND				0,125	7700
Manganese (Mn)	ND				0,125	15000
Nickel (Ni)	ND				0,125	930
Strontium (Sr)	ND				0,125	56000
Tin (Sn)	ND				1,25	180000
Organic tin **	ND				0,125	12
Zinc (Zn)	ND				0,125	46000

\*\*= Unless the test results were marked with "#" or "Δ", Chromium (III) & Chromium (VI) and Organic tin contents were not directly determined and were derived from migration results of total chromium and tin respectively.

# = Confirmation of Chromium (VI) test was performed on the tested component. And the reported value of migration of Chromium (III) = migration value of total Chromium - migration value of Chromium(VI).

Δ = Confirmation test was performed on the tested component. The reported value was the sum of the migration values of Organotins which are specified Table 3 and Annex J -Table J.1 after converted to Tributyl tin by calculation.

ppm (Part per million)

=mg / kg

<

=Less Than

ND

=Not Detected

## END OF TEST REPORT ##