AZOLAB LABORATUVAR HIZMETLERI A. Ş.
Adnan Kahveci Mah. Çankaya Cad. Simay Çarşı No:3 D1/34
Beylikdüzü/İSTANBUL
Tel: 0212 855 85 06(07) Fax: 0212 909 14 30
Web: www.azolab.com.tr E-mail: info@azolab.com.tr

Test
TS EN ISO/IEC 17025
AB-1110-T

AB-1110-T
2600035307
09-26

TEST REPORT

Report Nr/Revision Nr	: 2600035307
Agency Name	: Bigpoint Kırtasiye San. ve Tic. Ltd. Şti.
Agency Adress	: Deliklikaya Mah. Kitabe Cad. No:5, ARNAVUTKÖY/İSTANBUL
Sample Accepted on	: 28.08.2026
Re-submitted/Re-confirmation Date	: -
Test Resulted Date	: 03.09.2026
Date Release Report	: 03.09.2026
Total Number of Pages	: 12
Sample ID	: YAĞLI PASTEL
Previous Report No	: -
Brand Name	: BİGPOİNT
Model / Item No	: BBP912 - BPP911
Disclaimer	: The analysis was carried out upon customer request.
Decision Rule	: 3-The simple acceptance rule was applied.
Conformity Assessment	: -

AZOLAB LABORATUVAR HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number AB-1110-T for TS EN ISO/IEC 17025:2017 as test laboratory.
Turkish Accreditation Agency (TURKAK) is a signatory to the European co-operation for Accreditation (EA) Multilateral Agreement (MLA) and to the International Laboratory Accreditation Cooperation (ILAC) Mutual Recognition Arrangement (MRA) for the recognition of testing reports.
The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.

Seal

AZOLAB LABORATUVAR HİZMETLERİ AZOLAB

Füsun Erol
Müşteri Temsilcisi / Customer Representative
03.09.2026
e-imzalıdır

Görkem EROĞLU
Hardlines Bölüm Müdürü / Hardlines Division Manager
03.09.2026
e-imzalıdır

This report shall not be reproduced or any part of used for any other purpose without the written permission of Azolab Laboratory.
Testing reports without signature are invalid.

This document has been electronically signed in accordance with the Electronic Signature Law No. 5070.

AZOLAB LABORATUVAR HIZMETLERI A. Ş.
Adnan Kahveci Mah. Çankaya Cad. Simay Çarşı No:3 D1/34
Beylikdüzü/İSTANBUL
Tel: 0212 855 85 06(07) Fax: 0212 909 14 30
Web: www.azolab.com.tr E-mail: info@azolab.com.tr

AB-1110-T
2600035307
09-26

TEST REPORT

	ANALYSIS	METHOD	RESULT
*	SAFETY OF TOYS – PART 1: MECHANICAL AND PHYSICAL PROPERTIES	TS EN 71-1+A1 :2018/BS EN 71-1:2014+A1:2018/ EN 71-1:2014+A1:2018 (WITHDRAWN)	P
*	EN 71-2-SAFETY OF TOYS-PART 2: FLAMMABILITY	TS EN 71-2+A1:2025 / BS EN 71-2:2020+A1:2025	P
*	DETERMINATION OF PHTHALATES	CPSC-CH-C1001.09:2018	P
*	DETERMINATION OF PAH's	AfPS GS:2019:01	P
*	SAFETY OF TOYS-PART 3: MIGRATION OF CERTAIN ELEMENTS - CATEGORY 3	EN 71-3:2019+A2:2024/BS EN 71 3:2019+ A2:2024/TS EN 71 3+A2:2025 K3	P
*	SAFETY OF TOYS-PART 3: MIGRATION OF CERTAIN ELEMENTS- CATEGORY 1	EN 71-3:2019+A2:2024/BS EN 71 3:2019+ A2:2024/TS EN 71 3+A2:2025 K1	P

REMARK: Test results, methods, and other information regarding the sample are provided on the pages of this report, based on the information specified by the customer in the "Analysis Request Form". The test results are valid for the samples mentioned above. They may not represent the lot to which the sample belongs. This report does not replace the "Product Certificate". Samples remaining after testing will be keep in conditions for the periods specified in the analysis request and offer forms. Physically, chemically and microbiologically decomposed samples are discarded regardless of the storage period. Applicant can not claim any right in this regard. The measurement uncertainty for the tests is reported upon customer request, but the measurement uncertainty value is not considered in the "Pass/Fail" evaluation. The reported return is obtained using a standard return coverage factor k=2 to determine whether the quantity is present or not. The confidence level is 95%. The decision rule requested by the customer is stated on the first page of the report. The declaration of conformity is issued according to the Simple Decision Rule (assessment of durability or non-conformity based solely on whether the test result obtained falls within the stated yields, without considering the confidence level and the uncertainty of the measurements). In the case of a different decision parameter, the applied test and measurement uncertainty are given and marked along with the results table. Analyses marked with '*' are within our scope accredited by TÜRKAK according to TS EN ISO/IEC 17025. Analyses marked with '**' were performed by an external laboratory accredited by TÜRKAK according to TS EN ISO/IEC 17025. It is stated that any additional notes regarding the analyses are not included on the relevant page of the report.

This document has been electronically signed in accordance with the Electronic Signature Law No. 5070.

AZOLAB LABORATUVAR HIZMETLERI A. Ş.
Adnan Kahveci Mah. Çankaya Cad. Simay Çarşı No:3 D1/34
Beylikdüzü/İSTANBUL
Tel: 0212 855 85 06(07) Fax: 0212 909 14 30
Web: www.azolab.com.tr E-mail: info@azolab.com.tr

AB-1110-T
2600035307
09-26

TEST REPORT

Photo of the sample received



AZOLAB LABORATUVAR HIZMETLERI A. Ş.
Adnan Kahveci Mah. Çankaya Cad. Simay Çarşı No:3 D1/34
Beylikdüzü/İSTANBUL
Tel: 0212 855 85 06(07) Fax: 0212 909 14 30
Web: www.azolab.com.tr E-mail: info@azolab.com.tr

AB-1110-T
2600035307
09-26

TEST REPORT

Photo of the sample received



AZOLAB LABORATUVAR HIZMETLERI A. Ş.
Adnan Kahveci Mah. Çankaya Cad. Simay Çarşı No:3 D1/34
Beylikdüzü/İSTANBUL
Tel: 0212 855 85 06(07) Fax: 0212 909 14 30
Web: www.azolab.com.tr E-mail: info@azolab.com.tr

AB-1110-T
2600035307
09-26

TEST REPORT

Sample ID	Part No.	Part ID	Explanatory Information
A-YAĞLI PASTEL 12 RENK B-YAĞLI PASTEL 24 RENK	Part 001	Dye pastel white	
B-YAĞLI PASTEL 24 RENK	Part 002	Dye pastel pale orange	
A-YAĞLI PASTEL 12 RENK B-YAĞLI PASTEL 24 RENK	Part 003	Dye pastel ochre	
B-YAĞLI PASTEL 24 RENK	Part 004	Dye pastel yellow	
A-YAĞLI PASTEL 12 RENK B-YAĞLI PASTEL 24 RENK	Part 005	Dye pastel chrome yellow	
B-YAĞLI PASTEL 24 RENK	Part 006	Dye pastel yellow orange	
A-YAĞLI PASTEL 12 RENK B-YAĞLI PASTEL 24 RENK	Part 007	Dye pastel vermillion	
A-YAĞLI PASTEL 12 RENK B-YAĞLI PASTEL 24 RENK	Part 008	Dye pastel red	
B-YAĞLI PASTEL 24 RENK	Part 009	Dye pastel deep modder	
B-YAĞLI PASTEL 24 RENK	Part 010	Dye pastel red brown	
B-YAĞLI PASTEL 24 RENK	Part 011	Dye pastel rose pink	
A-YAĞLI PASTEL 12 RENK B-YAĞLI PASTEL 24 RENK	Part 012	Dye pastel violet	
B-YAĞLI PASTEL 24 RENK	Part 013	Dye pastel dark brown	
B-YAĞLI PASTEL 24 RENK	Part 014	Dye pastel prussian blue	
B-YAĞLI PASTEL 24 RENK	Part 015	Dye pastel ultramarine blue	
A-YAĞLI PASTEL 12 RENK B-YAĞLI PASTEL 24 RENK	Part 016	Dye pastel cobalt blue	
A-YAĞLI PASTEL 12 RENK B-YAĞLI PASTEL 24 RENK	Part 017	Dye pastel sky blue	
B-YAĞLI PASTEL 24 RENK	Part 018	Dye pastel cobalt green	
A-YAĞLI PASTEL 12 RENK B-YAĞLI PASTEL 24 RENK	Part 019	Dye pastel deep green	
B-YAĞLI PASTEL 24 RENK	Part 020	Dye pastel kadmium green	
A-YAĞLI PASTEL 12 RENK B-YAĞLI PASTEL 24 RENK	Part 021	Dye pastel yellow green	
B-YAĞLI PASTEL 24 RENK	Part 022	Dye pastel olive	
A-YAĞLI PASTEL 12 RENK B-YAĞLI PASTEL 24 RENK	Part 023	Dye pastel bluish gray	
A-YAĞLI PASTEL 12 RENK B-YAĞLI PASTEL 24 RENK	Part 024	Dye pastel black	
A-YAĞLI PASTEL 12 RENK B-YAĞLI PASTEL 24 RENK	Part 025	Cellophane coated multicolour printed box	
A-YAĞLI PASTEL 12 RENK B-YAĞLI PASTEL 24 RENK	Part 026	Plastic black inner box	
A-YAĞLI PASTEL 12 RENK B-YAĞLI PASTEL 24 RENK	Part 027	Sponge white inner cover	
A-YAĞLI PASTEL 12 RENK B-YAĞLI PASTEL 24 RENK	Part 028	Paper multicolour printed dye covers	
A-YAĞLI PASTEL 12 RENK	Part 029	YAĞLI PASTEL 12 RENK	
B-YAĞLI PASTEL 24 RENK	Part 030	YAĞLI PASTEL 24 RENK	

Summary of Results

Parts & Results															
Parts	**001**	**002**	**003**	**004**	**005**	**006**	**007**	**008**	**009**	**010**	**011**	**012**	**013**	**014**	**015**

P: Pass F: Fail ND: Not Detected X:-:NA: Not Applicable LS: Lack of Sample NR: No Requirement SC: Still Continue I: Inconclusive

AZOLAB LABORATUVAR HIZMETLERI A. Ş.
Adnan Kahveci Mah. Çankaya Cad. Simay Çarşı No:3 D1/34
Beylikdüzü/İSTANBUL
Tel: 0212 855 85 06(07) Fax: 0212 909 14 30
Web: www.azolab.com.tr E-mail: info@azolab.com.tr

TEST REPORT

*SAFETY OF TOYS – PART 1: MECHANICAL AND PHYSICAL PROPERTIES	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
*EN 71-2-SAFETY OF TOYS-PART 2: FLAMMABILITY	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
*DETERMINATION OF PHTHALATES	P	P	P	P	P	P	P	P	P	P	P	P	P	P	P
*DETERMINATION OF PAH's	P	P	P	P	P	P	P	P	P	P	P	P	P	P	P
*SAFETY OF TOYS-PART 3: MIGRATION OF CERTAIN ELEMENTS -CATEGORY 3	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
*SAFETY OF TOYS-PART 3: MIGRATION OF CERTAIN ELEMENTS-CATEGORY 1	P	P	P	P	P	P	P	P	P	P	P	P	P	P	P

Summary of Results

Parts & Results															
Parts	**016**	**017**	**018**	**019**	**020**	**021**	**022**	**023**	**024**	**025**	**026**	**027**	**028**	**029**	**030**
*SAFETY OF TOYS – PART 1: MECHANICAL AND PHYSICAL PROPERTIES	X	X	X	X	X	X	X	X	X	X	X	X	X	P	P
*EN 71-2-SAFETY OF TOYS-PART 2: FLAMMABILITY	X	X	X	X	X	X	X	X	X	X	X	X	X	P	P
*DETERMINATION OF PHTHALATES	P	P	P	P	P	P	P	P	P	P	P	P	X	X	X
*DETERMINATION OF PAH's	P	P	P	P	P	P	P	P	P	P	P	P	X	X	X
*SAFETY OF TOYS-PART 3: MIGRATION OF CERTAIN ELEMENTS -CATEGORY 3	X	X	X	X	X	X	X	X	X	P	P	P	P	X	X
*SAFETY OF TOYS-PART 3: MIGRATION OF CERTAIN ELEMENTS-CATEGORY 1	P	P	P	P	P	P	P	P	P	X	X	X	X	X	X

P: Pass F: Fail ND: Not Detected X:-:NA: Not Applicable LS: Lack of Sample NR: No Requirement SC: Still Continue I: Inconclusive

AZOLAB LABORATUVAR HIZMETLERI A. Ş.
Adnan Kahveci Mah. Çankaya Cad. Simay Çarşı No:3 D1/34
Beylikdüzü/İSTANBUL
Tel: 0212 855 85 06(07) Fax: 0212 909 14 30
Web: www.azolab.com.tr E-mail: info@azolab.com.tr

AB-1110-T
2600035307
09-26

TEST REPORT

***SAFETY OF TOYS – PART 1: MECHANICAL AND PHYSICAL PROPERTIES**
A [029] / TS EN 71-1+A1 :2018/BS EN 71-1:2014+A1:2018/ EN 71-1:2014+A1:2018 (WITHDRAWN)
This report details the clauses appropriate to this item. Those clauses not referred to were considered not applicable.

- Age Group Which Indicated : +36 month
- Laboratory Age Grading : +36 month
- Tested Age Group : +36 month
The item was tested for children aged over 36 months according to standard.

Matter	Result
*4. GENERAL REQUIREMENTS	Pass
*4.1 Material Cleanliness	Pass
*4.7 Edges	Pass (a+c)
*4.8 Points And Metallic Wires	Pass (a+e)
*7. WARNINGS, MARKINGS AND INSTRUCTIONS FOR USE	Relevant ##
*7.1 General	Relevant
*7.2 Toys Not Intended For Children Under 36 Months	Relevant

The text of this note is for information only and the indents do not constitute requirements of this European Standard. The information is not exhaustive and Directive 2009/48/EC and the associated guidance documents should be consulted for further details.

The toy or, its packaging or document accompanying must be labelled with:
** The name and address of the manufacturer **(Present)**
** The name and address of the importer **(Present)**
Type, batch, serial or model number or other element allowing of toy identification **(Present)**
The following advisory note: ‘‘Retain for future reference’’, if the information is not on the toy itself **(Present)**
A CE mark in the correct shape and size. **(Present)**
- Warning and other information should be in the national language(s) of the countries where the toy is marketed.

** In the case of the toy sell in European countries, the toy, its packaging or document accompanying must be labelled with the name and address of the manufacturer and importer.

***SAFETY OF TOYS – PART 1: MECHANICAL AND PHYSICAL PROPERTIES**
B [030] / TS EN 71-1+A1 :2018/BS EN 71-1:2014+A1:2018/ EN 71-1:2014+A1:2018 (WITHDRAWN)
This report details the clauses appropriate to this item. Those clauses not referred to were considered not applicable.

- Age Group Which Indicated : +36 month
- Laboratory Age Grading : +36 month
- Tested Age Group : +36 month
The item was tested for children aged over 36 months according to standard.

Matter	Result
*4. GENERAL REQUIREMENTS	Pass
*4.1 Material Cleanliness	Pass
*4.7 Edges	Pass (a+c)
*4.8 Points And Metallic Wires	Pass (a+e)
*7. WARNINGS, MARKINGS AND INSTRUCTIONS FOR USE	Relevant ##
*7.1 General	Relevant
*7.2 Toys Not Intended For Children Under 36 Months	Relevant

The text of this note is for information only and the indents do not constitute requirements of this European Standard. The information is not exhaustive and Directive 2009/48/EC and the associated guidance documents should be consulted for further details.

The toy or, its packaging or document accompanying must be labelled with:
** The name and address of the manufacturer **(Present)**
** The name and address of the importer **(Present)**
Type, batch, serial or model number or other element allowing of toy identification **(Present)**
The following advisory note: ‘‘Retain for future reference’’, if the information is not on the toy itself **(Present)**
A CE mark in the correct shape and size. **(Present)**
- Warning and other information should be in the national language(s) of the countries where the toy is marketed.

** In the case of the toy sell in European countries, the toy, its packaging or document accompanying must be labelled with the name and address of the manufacturer and importer.

AZOLAB LABORATUVAR HIZMETLERI A. Ş.
Adnan Kahveci Mah. Çankaya Cad. Simay Çarşı No:3 D1/34
Beylikdüzü/İSTANBUL
Tel: 0212 855 85 06(07) Fax: 0212 909 14 30
Web: www.azolab.com.tr E-mail: info@azolab.com.tr

AB-1110-T
2600035307
09-26

TEST REPORT

***EN 71-2-SAFETY OF TOYS-PART 2: FLAMMABILITY**
A [029] / TS EN 71-2+A1:2025 / BS EN 71-2:2020+A1:2025
This report details the clauses appropriate to this item. Those clauses not referred to were considered not applicable.

NOTE 1: Extremely flammable liquids, high flammable liquids and flammable gases can not be tested.

Matter	Result
*4. RULES	Pass
*4.1 General Rules #(See Note 1,2)	Pass

 # NOTE 2: 4.1 Parameters Considered For General Requirements
Cellulose nitrate
Washing Process ** : Not applied
**(Cleaning process apply to the product in necessary situtations for appropriate clauses of EN 71-2 according to instructions that given on toy or if there is no instructions apply pursuant to indicate in standard.)
Type of Gas : Butane Gas (Gas which used in test burner)
The test results thus obtained can not be considered as providing an overall indication of the potential fire hazard of toys or materials when subjected to other sources of ignition.
Condition Parameters: 65±5 %RH ; 20±5°C at least 7 hour
Test Atmosphere: 10°C - 30°C / 15-80 %RH

***EN 71-2-SAFETY OF TOYS-PART 2: FLAMMABILITY**
B [030] / TS EN 71-2+A1:2025 / BS EN 71-2:2020+A1:2025
This report details the clauses appropriate to this item. Those clauses not referred to were considered not applicable.

NOTE 1: Extremely flammable liquids, high flammable liquids and flammable gases can not be tested.

Matter	Result
*4. RULES	Pass
*4.1 General Rules #(See Note 1,2)	Pass

 # NOTE 2: 4.1 Parameters Considered For General Requirements
Cellulose nitrate
Washing Process ** : Not applied
**(Cleaning process apply to the product in necessary situtations for appropriate clauses of EN 71-2 according to instructions that given on toy or if there is no instructions apply pursuant to indicate in standard.)
Type of Gas : Butane Gas (Gas which used in test burner)
The test results thus obtained can not be considered as providing an overall indication of the potential fire hazard of toys or materials when subjected to other sources of ignition.
Condition Parameters: 65±5 %RH ; 20±5°C at least 7 hour
Test Atmosphere: 10°C - 30°C / 15-80 %RH

AZOLAB LABORATUVAR HIZMETLERI A. Ş.
Adnan Kahveci Mah. Çankaya Cad. Simay Çarşı No:3 D1/34
Beylikdüzü/İSTANBUL
Tel: 0212 855 85 06(07) Fax: 0212 909 14 30
Web: www.azolab.com.tr E-mail: info@azolab.com.tr

AB-1110-T
2600035307
09-26

TEST REPORT

***DETERMINATION OF PHTHALATES**
CPSC-CH-C1001.09:2018

Analyzed by: GC-MS

Controlled Compounds	CAS Number	Part 001+ 002+003	Part 004+ 005+006	Part 007+ 008+009	Part 010+ 011+012	Part 013+ 014+015	Part 016+ 017+018	Part 019+ 020+021	Part 022+ 023+024	Reporting Limit (mg/kg)
*Di-iso-nonyl phthalate (DINP)	28553-12-0/68515-48-0	<60	<60	<60	<60	<60	<60	<60	<60	60
*Di-n-octylphthalate (DNOP)	117-84-0	<60	<60	<60	<60	<60	<60	<60	<60	60
*Di-(2-ethylhexyl)-phtalete (DEHP)	117-81-7	<60	<60	<60	<60	<60	<60	<60	<60	60
*Di-isodecyl phtalate (DIDP)	26761-40-0/68515-49-1	<60	<60	<60	<60	<60	<60	<60	<60	60
*Butylbenzyl phthalate (BBP)	85-68-7	<60	<60	<60	<60	<60	<60	<60	<60	60
*Dibutyl phthalate (DBP)	84-74-2	<60	<60	<60	<60	<60	<60	<60	<60	60
*TOTAL(DBP+ DEHP+ BBP)		<60	<60	<60	<60	<60	<60	<60	<60	60
*TOTAL (DINP+ DNOP+ DIDP)		<60	<60	<60	<60	<60	<60	<60	<60	60
	Result	Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass	

Controlled Compounds	CAS Number	Part 025	Part 026	Part 027						Reporting Limit (mg/kg)
*Di-iso-nonyl phthalate (DINP)	28553-12-0/68515-48-0	<60	<60	<60						60
*Di-n-octylphthalate (DNOP)	117-84-0	<60	<60	<60						60
*Di-(2-ethylhexyl)-phtalete (DEHP)	117-81-7	<60	<60	<60						60
*Di-isodecyl phtalate (DIDP)	26761-40-0/68515-49-1	<60	<60	<60						60
*Butylbenzyl phthalate (BBP)	85-68-7	<60	<60	<60						60
*Dibutyl phthalate (DBP)	84-74-2	<60	<60	<60						60
*TOTAL(DBP+ DEHP+ BBP)		<60	<60	<60						60
*TOTAL (DINP+ DNOP+ DIDP)		<60	<60	<60						60
	Result	Pass	Pass	Pass						

Forbidden Compounds : LIMIT (MAX.) = Each Compounds 1000ppm; Total DBP, DEHP, BBP < 1000 ppm; Total DINP, DNOP, DIDP < 1000 ppm
Limit Value :It is given by the EU Regulation 1907/2006 (REACH), Annex XVII Entry 51&52

AZOLAB LABORATUVAR HIZMETLERI A. Ş.
Adnan Kahveci Mah. Çankaya Cad. Simay Çarşı No:3 D1/34
Beylikdüzü/İSTANBUL
Tel: 0212 855 85 06(07) Fax: 0212 909 14 30
Web: www.azolab.com.tr E-mail: info@azolab.com.tr

AB-1110-T
2600035307
09-26

TEST REPORT

***SAFETY OF TOYS-PART 3: MIGRATION OF CERTAIN ELEMENTS -CATEGORY 3**
EN 71-3:2019+A2:2024/BS EN 71 3:2019+A2:2024/TS EN 71 3+A2:2025 K3

Analyzed by: ICP-MS

Controlled Compounds	CAS Number	Part 025	Part 026	Part 027	Part 028	Limiting Value (mg/kg)	Reporting Limit (mg/kg)
*Aluminium (Al)	7429-90-5	40	<0,125	<0,125	<0,125	28130	0,125
*Antimony (Sb)	7440-36-0	<0,125	<0,125	<0,125	<0,125	560	0,125
*Arsenic (As)	7440-38-2	<0,125	<0,125	<0,125	<0,125	47	0,125
*Copper (Cu)	7440-50-8	<0,125	<0,125	<0,125	<0,125	7700	0,125
*Barium (Ba)	7440-39-3	<0,125	<0,125	<0,125	<0,125	18750	0,125
*Boron (B)	7440-42-8	<0,125	<0,125	<0,125	<0,125	15000	0,125
*Mercury (Hg)	7439-97-6	<0,0125	<0,0125	<0,0125	<0,0125	94	0,0125
*Zinc (Zn)	7440-66-6	<0,125	<0,125	<0,125	<0,125	46000	0,125
*Cadmium (Cd)	7440-43-9	<0,125	<0,125	<0,125	<0,125	17	0,125
*Tin (Sn)	7440-31-5	<0,125	<0,125	<0,125	<0,125	180000	0,125
*Cobalt (Co)	7440-48-4	<0,125	<0,125	<0,125	<0,125	130	0,125
*Chromium (Cr +3)	7440-47-3	<0,47	<0,47	<0,47	<0,47	460	0,47
*Chromium (Cr +6)	18540-29-9	<0,001	<0,001	<0,001	<0,001	0,053	0,001
*Lead (Pb)	7439-92-1	<0,125	<0,125	<0,125	<0,125	23	0,125
*Manganese (Mn)	7439-96-5	<0,125	<0,125	20	<0,125	15000	0,125
*Nickel (Ni)	7440-02-0	<0,125	<0,125	<0,125	<0,125	930	0,125
*Selenium (Se)	7782-49-2	<0,125	<0,125	<0,125	<0,125	460	0,125
*Strontium (Sr)	7440-24-6	22	<0,125	26	<0,125	56000	0,125
Organic Tin	-	<0,02	<0,02	<0,02	<0,02	12	0,02
	Result	Pass	Pass	Pass	Pass		

Limit Value : It is given by Safety of toys Part 3: Migration of certain elements- Scraped-off Materials, Category 3.

***SAFETY OF TOYS-PART 3: MIGRATION OF CERTAIN ELEMENTS-CATEGORY 1**
EN 71-3:2019+A2:2024/BS EN 71 3:2019+A2:2024/TS EN 71 3+A2:2025 K1

Analyzed by: ICP-MS

AZOLAB LABORATUVAR HIZMETLERI A. Ş.
Adnan Kahveci Mah. Çankaya Cad. Simay Çarşı No:3 D1/34
Beylikdüzü/İSTANBUL
Tel: 0212 855 85 06(07) Fax: 0212 909 14 30
Web: www.azolab.com.tr E-mail: info@azolab.com.tr

AB-1110-T
2600035307
09-26

TEST REPORT

Controlled Compounds	CAS Number	Part 001	Part 002	Part 003	Part 004	Part 005	Part 006	Part 007	Part 008	Limiting Value (mg/kg)	Reporting Limit (mg/kg)
*Aluminium (Al)	7429-90-5	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	2250	0,125
*Antimony (Sb)	7440-36-0	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	45	0,125
*Arsenic (As)	7440-38-2	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	3,8	0,125
*Copper (Cu)	7440-50-8	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	622,5	0,125
*Barium (Ba)	7440-39-3	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	1500	0,125
*Boron (B)	7440-42-8	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	1200	0,125
*Mercury (Hg)	7439-97-6	<0,0125	<0,0125	<0,0125	<0,0125	<0,0125	<0,0125	<0,0125	<0,0125	7,5	0,0125
*Zinc (Zn)	7440-66-6	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	3750	0,125
*Cadmium (Cd)	7440-43-9	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	1,3	0,125
*Tin (Sn)	7440-31-5	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	15000	0,125
*Cobalt (Co)	7440-48-4	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	10,5	0,125
*Chromium III	7440-47-3	<0,47	<0,47	<0,47	<0,47	<0,47	<0,47	<0,47	<0,47	37,5	0,47
*Chromium VI	18540-29-9	<0,001	<0,001	<0,001	<0,001	<0,001	<0,001	<0,001	<0,001	0,02	0,001
*Lead (Pb)	7439-92-1	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	2,0	0,125
*Manganese (Mn)	7439-96-5	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	1200	0,125
*Nickel (Ni)	7440-02-0	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	75	0,125
*Selenium (Se)	7782-49-2	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	37,5	0,125
*Strontium (Sr)	7440-24-6	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	4500	0,125
Organotin Tin	-	<0,02	<0,02	<0,02	<0,02	<0,02	<0,02	<0,02	<0,02	0,9	0,02
	Result	Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass		

Controlled Compounds	CAS Number	Part 009	Part 010	Part 011	Part 012	Part 013	Part 014	Part 015	Part 016	Limiting Value (mg/kg)	Reporting Limit (mg/kg)
*Aluminium (Al)	7429-90-5	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	2250	0,125
*Antimony (Sb)	7440-36-0	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	45	0,125
*Arsenic (As)	7440-38-2	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	3,8	0,125
*Copper (Cu)	7440-50-8	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	622,5	0,125
*Barium (Ba)	7440-39-3	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	1500	0,125
*Boron (B)	7440-42-8	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	1200	0,125
*Mercury (Hg)	7439-97-6	<0,0125	<0,0125	<0,0125	<0,0125	<0,0125	<0,0125	<0,0125	<0,0125	7,5	0,0125
*Zinc (Zn)	7440-66-6	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	3750	0,125
*Cadmium (Cd)	7440-43-9	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	1,3	0,125
*Tin (Sn)	7440-31-5	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	15000	0,125
*Cobalt (Co)	7440-48-4	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	10,5	0,125
*Chromium III	7440-47-3	<0,47	<0,47	<0,47	<0,47	<0,47	<0,47	<0,47	<0,47	37,5	0,47
*Chromium VI	18540-29-9	<0,001	<0,001	<0,001	<0,001	<0,001	<0,001	<0,001	<0,001	0,02	0,001
*Lead (Pb)	7439-92-1	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	2,0	0,125
*Manganese (Mn)	7439-96-5	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	1200	0,125
*Nickel (Ni)	7440-02-0	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	75	0,125
*Selenium (Se)	7782-49-2	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	37,5	0,125
*Strontium (Sr)	7440-24-6	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	4500	0,125
Organotin Tin	-	<0,02	<0,02	<0,02	<0,02	<0,02	<0,02	<0,02	<0,02	0,9	0,02
	Result	Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass		

Controlled Compounds	CAS Number	Part 017	Part 018	Part 019	Part 020	Part 021	Part 022	Part 023	Part 024	Limiting Value (mg/kg)	Reporting Limit (mg/kg)
*Aluminium (Al)	7429-90-5	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	2250	0,125
*Antimony (Sb)	7440-36-0	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	45	0,125
*Arsenic (As)	7440-38-2	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	3,8	0,125
*Copper (Cu)	7440-50-8	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	622,5	0,125
*Barium (Ba)	7440-39-3	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	1500	0,125
*Boron (B)	7440-42-8	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	1200	0,125
*Mercury (Hg)	7439-97-6	<0,0125	<0,0125	<0,0125	<0,0125	<0,0125	<0,0125	<0,0125	<0,0125	7,5	0,0125
*Zinc (Zn)	7440-66-6	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	3750	0,125
*Cadmium (Cd)	7440-43-9	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	1,3	0,125
*Tin (Sn)	7440-31-5	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	15000	0,125
*Cobalt (Co)	7440-48-4	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	10,5	0,125
*Chromium III	7440-47-3	<0,47	<0,47	<0,47	<0,47	<0,47	<0,47	<0,47	<0,47	37,5	0,47

P: Pass F: Fail ND: Not Detected X:-:NA: Not Applicable LS: Lack of Sample NR: No Requirement SC: Still Continue I: Inconclusive

AZOLAB LABORATUVAR HIZMETLERI A. Ş.
Adnan Kahveci Mah. Çankaya Cad. Simay Çarşı No:3 D1/34
Beylikdüzü/İSTANBUL
Tel: 0212 855 85 06(07) Fax: 0212 909 14 30
Web: www.azolab.com.tr E-mail: info@azolab.com.tr

AB-1110-T
2600035307
09-26

TEST REPORT

*Chromium VI	18540-29-9	<0,001	<0,001	<0,001	<0,001	<0,001	<0,001	<0,001	<0,001	0,02	0,001
*Lead (Pb)	7439-92-1	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	2,0	0,125
*Manganese (Mn)	7439-96-5	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	1200	0,125
*Nickel (Ni)	7440-02-0	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	75	0,125
*Selenium (Se)	7782-49-2	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	37,5	0,125
*Strontium (Sr)	7440-24-6	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	<0,125	4500	0,125
Organotin Tin	-	<0,02	<0,02	<0,02	<0,02	<0,02	<0,02	<0,02	<0,02	0,9	0,02
	Result	Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass		

Limit Value : It is given by Safety of toys Part 3: Migration of certain elements- Dry, Fragile, Category 1.

***DETERMINATION OF PAH's**
AfPS GS:2019:01

Analyzed by: GC-MS

Controlled Compounds	CAS Number	Part 001+ 002+003	Part 004+ 005+006	Part 007+ 008+009	Part 010+ 011+012	Part 013+ 014+015	Part 016+ 017+018	Part 019+ 020+021	Part 022+ 023+024	Limiting Value (mg/kg)	Reporting Limit (mg/kg)
*Benzo(e)pyrene	192-97-2	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	0,5	0,1
*Benzo[j]fluoranthene	205-82-3	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	0,5	0,1
*Benz[a]anthracene	56-55-3	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	0,5	0,1
*Benzo[k]fluoranthene	207-08-9	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	0,5	0,1
*Benzo[a]pyrene	50-32-8	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	0,5	0,1
*Chrysene	218-01-9	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	0,5	0,1
*Dibenz[a,h]anthracene	53-70-3	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	0,5	0,1
*Benz[b]fluoranthene	205-99-2	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	<0,1	0,5	0,1
	Result	Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass		

Controlled Compounds	CAS Number	Part 025	Part 026	Part 027						Limiting Value (mg/kg)	Reporting Limit (mg/kg)
*Benzo(e)pyrene	192-97-2	<0,1	<0,1	<0,1						0,5	0,1
*Benzo[j]fluoranthene	205-82-3	<0,1	<0,1	<0,1						0,5	0,1
*Benz[a]anthracene	56-55-3	<0,1	<0,1	<0,1						0,5	0,1
*Benzo[k]fluoranthene	207-08-9	<0,1	<0,1	<0,1						0,5	0,1
*Benzo[a]pyrene	50-32-8	<0,1	<0,1	<0,1						0,5	0,1
*Chrysene	218-01-9	<0,1	<0,1	<0,1						0,5	0,1
*Dibenz[a,h]anthracene	53-70-3	<0,1	<0,1	<0,1						0,5	0,1
*Benz[b]fluoranthene	205-99-2	<0,1	<0,1	<0,1						0,5	0,1
	Result	Pass	Pass	Pass							

Limit Value :It is given by the EU Regulation 1907/2006 (REACH), Annex XVII Entry 50