



TEST REPORT

Page 1 of 8

REPORT NUMBER : TURT251140796
APPLICANT NAME Bigpoint Kırtasiye San. ve Tic.Ltd.Şti.
ADDRESS Merkez Mah. 29 Ekim Cad.No:53 Bahçelievler/İstanbul
Attention : Tel: 0212 551 00 92, Fax:0212 551 09 57
Efe Yüksel (efe@bigpoint.com.tr)
SAMPLE DESCRIPTION : Two samples of Bigpoint Black Coloured Sampler and Samples Set
DATE IN : 13 December, 2025
DATE OUT : 18 December, 2025
BRAND : BIGPOINT
ITEM NO : BP306-95
MANUFACTURER NAME : NINGBO HOOBN OFFICE SUPPLIES CO. LTD
COUNTRY OF ORIGIN : CHINA
SAMPLE PHOTOS :



PP

Seda Ekinci

Gaye CALIŞKAN
Customer Care Executive

Emre ÇALIK
Chemical Laboratory Manager

Intertek Test Hizmetleri A.S.
Merkez Mahallesi Sanayi Cad. No: 23 Altındağ Plaza Yenibosna 34197 - ISTANBUL / TURKEY
Phone : +90.212. 496 46 46 Fax : +90.212. 452 80 55
e-mail : intertekcg.turkiye@intertek.com
www.intertek-turkey.com



251140796

R E S U L T S

REPORT: TURT251140796

18 December, 2025

Part No	Tested Part
1	Black plastic body
2	Silver metal print
3	Silver metal long part
4	Silver metal short part
5	Silver metal smal part
6	Silver metal long spring
7	Silver metal big spring
8	Silver metal smal spring
9	Gerey metal big part
10	Gerey metal concealer
11	Gerey metal long cylindir
12	Gerey metal smal cylindir
13	Silver metal staples wire
14	Multicolor paper box
15	White/grey paper inner

Remark: Only suitable parts tested for the related tests.

RESULTS

REPORT: TURT251140796

18 December, 2025

Remark: Only suitable parts tested for the related tests.

Analysis Parameter	Reference Analysis Method	PASS	FAIL	Norm Limit	Standard for Norm Limit	Failed Item
DETERMINATION OF CERTAIN AROMATIC AMINES DERIVED FROM AZO	EN ISO 14362-1 determined by GC-MS, HPLC-MS	NA	NA	<30 ppm	REACH ANNEX XVII	-
POLYCYCLIC AROMATIC HYDROCARBONS (PAHS) ANALYSIS	In-House Method – "IHTM AL.2.032 Rev.15" (Based on AfPS GS and EN 17132) (Using GC-MS)	P	-	1 ppm	REACH ANNEX XVII	-
DETERMINATION OF CADMIUM CONTENT	In-House Method – "IHTM AL.2.222. Rev.10" (With reference to EPA 3050B, EPA 3051A, EPA 3052) (Using ICP-OES)	P	-	Metal, Plastic 100 ppm; Coating, print, dye 1000 ppm	REACH ANNEX XVII	-
DETERMINATION OF LEAD CONTENT	In-House Method – "IHTM AL.2.222. Rev.10" (With reference to EPA 3050B, EPA 3051A, EPA 3052) (Using ICP-OES)	P	-	500 ppm (0.05%)	REACH ANNEX XVII	-
TRIBUTYLTIN (TBT) CONTENT	In-House Method – "IHTM AL.2.030 Rev.13" (based on ISO 17353) (Using GC-MS)	P	-	1000 ppm (0.1%)	REACH ANNEX XVII	-
RELEASE OF NICKEL FOR COATED ITEM	BS EN 12472 & EN 1811 by ICP-MS Determination	NA	NA	<0.88	REACH ANNEX XVII	-
DMFU CONTENT	IHTM AL.2.136 By Solvent Extraction and Chromatographic Analysis using Mass Spectrometry (GC-MS)	NA	NA	1000 ppm (0.1%)	REACH ANNEX XVII	-
DETERMINATION OF BISPHENOL A (BPA) CONTENT	IHTM AL.2.330	NA	NA	No Requirement	REACH ANNEX XVII	-
DETERMINATION OF CR+VI CONTENT	ISO 17075-2 with HPLC Determination	NA	NA	3 ppm	REACH ANNEX XVII	-
DETERMINATION OF DIETHYLENE GLYCOL MONOBUTYL (DEGBE)	IHTM AL.2.409 refer to EPA 5000 & EPA 5021A with Headspace GC/MS	NA	NA	≤(3%)	REACH ANNEX XVII	-
TOLUENE CONTENT	IHTM AL.2.409 refer to EPA 5000 & EPA 5021A with Headspace GC/MS	NA	NA	≤1000 ppm (0.1%)	REACH ANNEX XVII	-
VINYL CHLORIDE MONOMER(VCM) CONTENT	IHTM AL.2.393 refer to ISO 6401 and GB/T 4615	NA	NA	No Requirement	REACH ANNEX XVII	-

AB-0716-T
TURT251140796
12-25

Page 4 of 8

RESULTS

REPORT: TURT251140796

18 December, 2025

RESULTS :

Analysis Parameter	Reference Analysis Method	PASS	FAIL	Norm Limit	Standard for Norm Limit	Failed Item
DETERMINATION OF LEAD CARBONATE / SULFATE CONTENT	IHTM AL.2.222 refer to USEPA 3050B / USEPA 3051A/ US EPA 3052 by acid digestion and determinated by ICP-OES	NA	NA	Not Detected	REACH ANNEX XVII	-

P = MEETS BUYER' S REQUIREMENT (GEÇTİ) / F = DOES NOT MEET BUYER' S REQUIREMENT (KALDI) / NR = NO REQUIREMENT (SINIR DEĞER BELİRTİLMEDİ) / SC=STILL CONTINUES (TEST İŞLEMİ DEVAM EDİYOR) / X=NOT PERFORMED (TEST EDİLMEDİ) / I = INCONCLUSIVE / NC = NO COMMENT / NA= NOT APPLICABLE

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Nor could it be used for PR activities. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>. Testing reports without signature are not valid. The sample has been provided by the customer and the results apply to the sample as received. Sample information is supplied by the customer. Unless otherwise requested, this laboratory applies shared risk decision rule. Unless otherwise is specified, all Pass or Fail results are given without uncertainty considered. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025 and TÜRKAK accreditation requirements.. Tests marked (*) in this test report are not included in the TÜRKAK accreditation schedule for this laboratory. Intertek accredited by TÜRKAK under registration number [AB-0716-T] for [TS EN ISO IEC 17025] as test laboratory. Turkish Accreditation Agency (TURKAK) is a signatory to the European co-operation for Accreditation (EA) Multilateral Agreement (MLA) and to the International Laboratory Accreditation Cooperation (ILAC) Mutual Recognition Arrangement (MRA) for the recognition of test reports.

R E S U L T S

REPORT: TURT251140796

18 December, 2025

POLYCYCLIC AROMATIC HYDROCARBONS (PAHs) ANALYSIS

In-House Method – “IHTM AL.2.032 Rev.15” (Based on AfPS GS and EN 17132) (Using GC-MS)

	Part 1	RESULT (mg/kg)	REQUIREMENT
1	Benzo (a) pyrene	Not Detected	1 ppm
2	Benzo (e) pyrene	Not Detected	1 ppm
3	Benzo (a) anthracene	Not Detected	1 ppm
4	Benzo (b) fluoranthene	Not Detected	1 ppm
5	Benzo (j) fluoranthene	Not Detected	1 ppm
6	Benzo (k) fluoranthene	Not Detected	1 ppm
7	Chrysene	Not Detected	1 ppm
8	Dibenzo (a,h) anthracene	Not Detected	1 ppm

ppm (part per million) = mg / kg
Detection Limit = 0.1 ppm

Estimated Total Uncertainty = (Textile:±15%, Plastic:±17%)

AB-0716-T
TURT251140796
12-25

Page 6 of 8

R E S U L T S

REPORT: TURT251140796

18 December, 2025

DETERMINATION OF CADMIUM CONTENT

In-House Method – “IHTM AL.2.222. Rev.10” (With reference to EPA 3050B, EPA 3051A, EPA 3052) (Using ICP-OES)

	RESULTS	REQUIREMENT
Part 1	Not Detected	100 ppm (0.01%)
Part 2	Not Detected	100 ppm (0.01%)
Part 14	Not Detected	100 ppm (0.01%)
Part 15	Not Detected	100 ppm (0.01%)

ppm: parts per million (mg/kg)
Detection Limit : 8 ppm

REMARK As per Lead Content Requirement in Annex XVII Entry 63, and Cadmium Content Requirement in Annex XVII Entry 23 of the REACH Regulation (EC) No:1907/2006 (Formerly Known as Directive 91/338/EEC), Acid Digestion Method was used Total Lead Content was determined by ICP-OES

Estimated Total Uncertainty=(Dye: ±16%, Glass: ±16%, Metal: ±16%, Plastic: ±16%, Textile: ±15%)

RESULTS

REPORT: TURT251140796

18 December, 2025

DETERMINATION OF LEAD CONTENT

In-House Method – “IHTM AL.2.222. Rev.10” (With reference to EPA 3050B, EPA 3051A, EPA 3052) (Using ICP-OES)

	RESULTS	REQUIREMENT
Part 1	Not Detected	500 ppm (0.05%)
Part 2	Not Detected	500 ppm (0.05%)
Part 3	Not Detected	500 ppm (0.05%)
Part 4	Not Detected	500 ppm (0.05%)
Part 5	Not Detected	500 ppm (0.05%)
Part 6	Not Detected	500 ppm (0.05%)
Part 7	Not Detected	500 ppm (0.05%)
Part 8	201 ppm	500 ppm (0.05%)
Part 9	Not Detected	500 ppm (0.05%)
Part 10	Not Detected	500 ppm (0.05%)
Part 11	Not Detected	500 ppm (0.05%)
Part 12	Not Detected	500 ppm (0.05%)
Part 13	Not Detected	500 ppm (0.05%)
Part 14	Not Detected	500 ppm (0.05%)
Part 15	Not Detected	500 ppm (0.05%)

ppm: parts per million (mg/kg)

Detection Limit : 8 ppm

REMARK As per Lead Content Requirement in Annex XVII Entry 63, and Cadmium Content Requirement in Annex XVII Entry 23 of the REACH Regulation (EC) No:1907/2006 (Formerly Known as Directive 91/338/EEC), Acid Digestion Method was used Total Lead Content was determined by ICP-OES

Estimated Total Uncertainty=(Dye: ±16%, Glass: ±16%, Metal: ±16%, Plastic: ±16%, Textile: ±15%)

AB-0716-T
TURT251140796
12-25

Page 8 of 8

R E S U L T S

REPORT: TURT251140796

18 December, 2025

TRIBUTYLTIN (TBT) CONTENT

In-House Method – “IHTM AL.2.030 Rev.13” (based on ISO 17353) (Using GC-MS)

ETHANOL EXTRACTION, DERIVATISATION AND ANALYSIS BY GAS CHROMATOGRAPHY - MASS SPECTROPHOTOMETRY

	RESULTS	REQUIREMENT
Part 1	Not Detected	1000 ppm (0.1%)
Part 2	Not Detected	1000 ppm (0.1%)

ppm: parts per million (mg/kg)
Detection Limit : 0.050 ppm

Estimated Total Uncertainty=(Plastic:±%19 ; Leather:±%19)**## END OF TEST REPORT ##**